



TECHNICAL DATA SHEET

FIRESPAN FSB Non-combustible Perforated Breather Membrane - Item No. FSB12540

ITEM	TEST STANDARD	UNIT	RESULT
Roll Width x Length	Actual	m	1.25 x 40
Roll Quantity	Actual	m2	50
Roll Weight	Actual	kg	12.5
DTS Non-combustible – NCC 2022	C2D10(6)(g)	-	Pass*
DTS Non-combustible	AS 1530.1	-	Pass*
Ignitability Index	AS 1530.3	-	0*
Spread of Flame Index	AS 1530.3	-	0*
Heat Evolved Index	AS 1530.3	-	0*
Smoke Developed Index	AS 1530.3	-	1*
DTS Non-combustible – NCC 2022	C2D10(6)(f)	-	Pass**
Flammability Index	AS 1530.2	-	1**
Material Thickness	Actual	mm	<1**
Duty / Tensile Strength	AS 4200.1	Classification	Extra Heavy
		kN/m	MD 27.0
		kN/m	LD 18.0
Edge Tear Resistance	AS 4200.1	Classification	Extra Heavy
		N (25mm)	MD 168
		N (25mm)	LD 206
Dry Delamination	AS 4201.1	-	Pass
Wet Delamination	AS 4201.2	-	Pass
Shrinkage	AS 4201.3	%	0.0
Water Barrier	AS 4201.4	Silver	Unclassified
		White	Unclassified
Emittance (Silver Foil Facing)	AS 4201.5	Value	0.05
	AS 4201.5	Reflectance	95%
Water Absorbency	AS 4201.6	g/m2	85.2
	10711500	Classification	Low
Vapour Transmission	ASTM E96	g/h.m2	4.325
		g/24h./m2	103.801
Vapour Permeance	ASTM E96	μg/N.s	0.774
Vapour Barrier	NCC 2019 (VCM)	Classification	Class 3
Vapour Resistance	ASTM E96	MN.s/g	(Low) 1.3
Burst Force	AS 2001.2.19	N	619
Bursting Strength	AS 4200.1	Classification	Light Wall
Durating Strength	A3 4200.1	Ciassilication	Ligiti vvali

^{*}Deemed-to-Satisfy non-combustible in accordance with AS 1530.1 and AS 1530.3 testing as per the requirements of NCC 2022 clause C2D10(6)(g). **Deemed-to-Satisfy non-combustible as per NCC 2022 clause C2D10(6)(f), with thickness <1mm and Flammability Index <5.

Installation Instructions: Install and tape in accordance with AS 4200.2 to provide a Deemed-to-Satisfy weatherproofing barrier in accordance with NCC 2022, Clause F3D3.

FIRESPAN FSS Technical Data Sheet (V1122) – **Page 1 of 1 Phone:** 1300 945 123 **Email:** sales@bluechipgroup.net.au | <u>Website</u> | <u>Disclaimer</u> | <u>Terms</u>